

Naturalan

Der robuste Natur-Designboden.

Natural fiber floor to click with HDF middle layer



Technical Data	
Plank format	Stone 915 x 620 x 9,0 mm
	Wood 1.815 x 305 x 9,0 mm
Packaging unit	Stone 4 planks/2,268 m ²
	Wood 4 planks/2,216 m ²
Palette content	Stone 44 cartons/99,792 m ²
	Wood 45 cartons/99,720 m ²
Surface	2-fold basic color application, digital printing, HotCoating PUR coating
Top layer	1,0 mm natural fiber
Carrier board	6,8 mm HDF
Underlay	1,2 mm Pressed cork impact sound insulation
Edge processing	4-sided super micro bevel
Laying method	Glueless UNICLIC technique
Testing Values	
Abraison resistance (EN 13329)	AC 5
Resilient flooring classification (EN 685)	23/33
Determination of burning behaviour	Cfl-s1 (EN-ISO 9239-1) • Does not release toxic gas during combustion
Resistance to chemicals (EN 423)	Very good resistance
Moisture proof	No
Mass per unit area (EN 430)	7.300 g/m ²
Suitable for underfloor heating	Yes (Hot water underfloor heating)
Light fastness (EN 105-Bo2)	> 7
Residual indentation (EN 433)	0,08 mm
Slip retardant (DIN 51130)	R 10
Suitable for caster chairs (EN 425)	Yes, with casters type W
Impact sound reduction (EN 140)	17 dB
Thermal conductivity (DIN-EN 52612-Teil 1)	0,08 m ² x K/W
Resistance to stubbed and burning cigarettes (EN 1399)	Yes
Disposal	Household waste or Second Life

